




CEWELD FL 160

TYPE	High basic SAW flux with low hydrogen content.			
APPLICATIONS	Boiler works, vessel and structural steel works, tanks and pressure vessels, offshore lifting applications, platforms etc..			
PROPERTIES	FL 160 is a highly basic SAW flux with low hydrogen content. Basicity: about 3 (according to Boniszewski) Current: DC or AC, in single or multi-wires Grain size: 2-20			
CLASSIFICATION	EN ISO	14174: SA FB 1 55 AC H5		
SUITABLE FOR	S355, S420, S460, X65, X70, X80			
APPROVALS	No Approvals Found			
WELDING POSITIONS	<div></div>			
TYPICAL CHEMICAL COMPOSITION IN WEIGHT (%)	Al2O3 20	CaF2 20	SiO2 15	CaO+MgO 40
REDRYING TEMPERATURE	Not required			
GAS ACCORDING EN 14175				

CEWELD FL 160

FL 160 0,2 - 2,0MM

Type	KG/unit	EANCode
Bag	25	8720663404008
Bag	25	8720663404015