



CEWELD SG CrMo1

TYPE	Copper coated welding wire for welding creep and hydrogen-resistant steels.(Type CrMo1, B2)														
APPLICATIONS	CEWELD® SG CRMo1 is suitable for boiler and pipe construction steels with 1.25% Cr and 0.5% Mo as well as for welding heat-treatable and case-hardening steels. The main areas of application are: High pressure boiler steels, offshore, repair, construction, pipelines, tubing etc.														
PROPERTIES	CEWELD® SG CRMo1 is Extreme easy to weld with excellent welding properties. Suitable to offer creep resistance for working temperatures up to 550 °C. The wire has low levels of tramp elements (eg. Sn, As, Sb and P) providing a low Bruscato Factor (X< 10 ppm) for temper embrittlement resistant application														
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.28: ER 80S-G</td> </tr> <tr> <td>EN ISO</td> <td>21952-A: G CrMo1Si</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>3</td> </tr> <tr> <td>W.Nr.</td> <td>1.7339</td> </tr> </table>	AWS	A 5.28: ER 80S-G	EN ISO	21952-A: G CrMo1Si	F-nr	6	FM	3	W.Nr.	1.7339				
AWS	A 5.28: ER 80S-G														
EN ISO	21952-A: G CrMo1Si														
F-nr	6														
FM	3														
W.Nr.	1.7339														
SUITABLE FOR	<p>Typ 1Cr0,5Mo, ISO 15608: ~5,1 1.7205, 1.7218, 1.7225, 1.7228, 1.7254, 1.7258, 1.7262, 1.7335, 1.7337, 1.7350, 1.7354, 1.7357, 1.7728 13CrMoV42, 13CrMo4-4, 13CrMo4-5, 15CrMo3, 15CrMo5, 13CrMoV42, 15Cr3, 16MnCr5, 20MnCr5, 15CrMo5, 24CrMo5, 25CrMo4, GS-22CrMo5, GS-22CrMo54, GS 17CrMo5-5, 16CrMoV4, 42CrMo4, 42CrMo4V, 41CrMo4V, ASTM A 182 Gr. F11 / F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11, P12; A 336 Gr. F11, F12; A 426 Gr. CP12 ; A 199; A200; A 387 Gr A11 / 12</p>														
APPROVALS	CE														
WELDING POSITIONS															
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.09</td> <td>0.6</td> <td>0.99</td> <td>0.006</td> <td>0.011</td> <td>1.18</td> <td>0.49</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Mo	0.09	0.6	0.99	0.006	0.011	1.18	0.49
C	Si	Mn	P	S	Cr	Mo									
0.09	0.6	0.99	0.006	0.011	1.18	0.49									
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} MPa</th> <th>R_m MPa</th> <th>A₅ (%)</th> <th>RT</th> <th>Impact Energy (J) ISO-V</th> </tr> </thead> <tbody> <tr> <td>620°C±15°C /1h</td> <td>400</td> <td>560</td> <td>22</td> <td>90</td> <td>-20°C 55</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	RT	Impact Energy (J) ISO-V	620°C±15°C /1h	400	560	22	90	-20°C 55		
Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	RT	Impact Energy (J) ISO-V										
620°C±15°C /1h	400	560	22	90	-20°C 55										
REDRYING TEMPERATURE	Not required														
GAS ACCORDING EN 14175	M21														



CEWELD SG CrMo1

SG CRM01 0,8MM

Type	KG/unit	EANCode
BS-300	15	8720663405821
D-100	1	8720663405852
D-200	5	8720663405838
D-200	3	8720663405845

SG CRM01 1,0MM

Type	KG/unit	EANCode
BS-300	15	8720663405869

SG CRM01 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663405876
Drum	250	8720663405890

SG CRM01 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663405883

SG CRM01 4,0MM

Type	KG/unit	EANCode
Drum	250	8720663405937