



# CEWELD OA 612

**TYPE** High alloyed fluxcored wire for hardfacing.

**APPLICATIONS** Bucket teeth, conveyors, cruscher hammers, coal mine cutters, mixer blades, mixer blades etc.


**PROPERTIES** This alloy offers very good resistance against general abrasion and heavy shock, all weld metal requires no buffer layer except on materials considered critical or in case of old hardfacing layers. In this Situation OA 4370, ER 100 S-G or OA MnCr is recommended. Suited for wear parts subject to strong impact, abrasion and shock. In critical cases the interpass temperature should be kept at 270°C for the best results. The weld metal is only machinable by grinding. Weldable without gas (open arc). (Also weldable under M21 mixed gas)

**CLASSIFICATION** EN ISO 14700: T Fe8  
DIN 8555: MF 6-GF-55-PR

**SUITABLE FOR** 54 HRc hardfacing alloy for wear resistant overlays, sand pumps, valve seats, dredger equipment, bucket teeth, stone crushing, hammers etc.

**APPROVALS** No Approvals Found

**WELDING POSITIONS**



**TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)**

C	Si	Mn	Cr	Fe
0.5	1	1.2	12.5	Rem.

**ALL WELD MECHANICAL PROPERTIES**

Heat Treatment	R <sub>p0,2</sub> MPa	R <sub>m</sub> MPa	A5 (%)	Hardness Rockwell C
As Welded /				Avg. 55

**REDRYING TEMPERATURE** 140°C / 24 hr

**GAS ACCORDING EN 14175**