






CEWELD OA 55 TC

TYPE	Titanium -alloyed tubular wire on a C-Cr-Ti carbide basis for hardfacing.						
APPLICATIONS	Rebuilding and or protecting wear parts that faces severe impact combined with heavy abrasion.						
PROPERTIES	Very good wear resistance against abrasion combined with impact. The deposit gives already a very good hardness in the second layer thanks to the Titanium carbides. The choice for the buffer layer is depending on the base metal and not always necessary.						
CLASSIFICATION	EN ISO DIN	14700: T Fe8 8555: MF 6-60-GP					
SUITABLE FOR	HRc 54-59, hardfacing alloy for Cement crusher rollers, Mineral and brick industry, Hammers, Screw conveyers, gravel pumps, bucket collars, dredger teeth etc.						
APPROVALS	No Approvals Found						
WELDING POSITIONS	<div> </div>						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Mo	Ti	Fe
	1.7	1.4	1	7.2	1.3	5	Rem.
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A5 (%)		Hardness Rockwell C	
	As Welded /					Avg. 58	
REDRYING TEMPERATURE	140°C / 24 hr						
GAS ACCORDING EN 14175							



CEWELD OA 55 TC

OA 55 TC 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663403421

OA 55 TC 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663403438

OA 55 TC 2,0MM

Type	KG/unit	EANCode
BS-300	15	8720663403445

OA 55 TC 2,8MM

Type	KG/unit	EANCode
BS-300	15	8720663403452