







# CEWELD AA 308H

TYPE	Rutile fluxcored stainless steel wire with high carbon content. ( Type 308H, 19 9 )							
APPLICATIONS	Welding stainless steel types with an alloy content between 16 to 21% Cr and 8 to 13 % Ni, with high carbon content. The names 18-8, 19-9, and 20-10 are often associated with filler metals of this classification.							
PROPERTIES	Smooth drop transfer and stable arc with no spatter losses. Excellent productivity and weldability, better wetting properties compared to solid wires.Excellent weld metal quality and X-ray soundness and excellent slag removal.Excellent for use in horizontal and down hand position							
CLASSIFICATION	AWS	A 5.22: E308HT0-4						
	AWS	A 5.22: E308HT0-1						
	EN ISO	17633-A: T 19 9 H R M21 3						
	F-nr	6						
	FM	5						
	W.Nr.	1.4302						
SUITABLE FOR	<b>ISO 15608: 8.1 Austenit ≤ 19 % Cr 9 % Ni, , TÜV 1000: Gr. 21</b> 1.4301, 1.4308, 1.6900, 1.6901, 1.6902, 1.6903, 1.9606 X 5 CrNi 18 10, X 5 CrNi 18 9, G-X 6 CrNi 18 9, X 12 CrNi 18 9, G-X 8 CrNi 18 10, X 6 CrNi 18 10, X 10 CrNiTi 18 10, X 5 CrNi 18 10 AISI 304, 304H, 312, 321H, 347, 347H, UNS S30409, S32109, S34709, S30400, S32100, S34700							
APPROVALS	CE							
WELDING POSITIONS	<div> PA</div> <div> PB</div> <div> PC</div> <div> PF</div>							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo
	0.06	0.9	1	0.015	0.008	19	10	0.3
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A5 (%)	Impact Energy (J) ISO-V			
	As Welded /	470	630	36	RT			
					80			
REDRYING TEMPERATURE	140°C / 24 hr							
GAS ACCORDING EN 14175	M21							