



CEWELD E CuAl8

TYPE Basic coated aluminium bronze electrode developed for welding on DC+. Good tensile strength alloy with good corrosion resistance.

APPLICATIONS CEWELD E CuAl8 is designed for joining steel with copper or its alloys and cladding steel or aluminium bronze.

PROPERTIES The weld deposit offers good wear and corrosion resistance even in seawater. Welding instructions:
- Preheating for sections >6 mm from 150 till 300 °C is recommended. Use the normal standard welding techniques.

CLASSIFICATION

AWS	A 5.6: ECuAl-A2
EN ISO	17777: E Cu 6100A
F-nr	31
W.Nr.	2.0926

SUITABLE FOR Aluminium bronze, Cladding steel, Shafts, Gliding surfaces, Joining steel to, Aluminium Bronze or Copper, etc.
Mat.n: 2.0916, 2.0920, 2.0928, 2.0460, 2.0932
CuAl5, CuAl8, G-CuAl9, CuZn20Al2, CuAl8Fe3,
UNS: C60600, C61000, C68700, C61400,
Copper-beryllium alloys Cu+0.5-2%Be, Cu-Zn brasses, Aluminum brass Cu22%,
Zn2%Al, Manganese bronzes Cu+20-45%Zn+1-3%Mn, Silicon
bronzes Cu+1-3.5%Si

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

Si	Mn	Fe	Pb	Al	Cu
0.7	0.5	0.8	0.01	7.5	Rem.

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{p0.2} MPa	R _m MPa	A5 (%)	Hardness Brinell Hardness
As Welded /	200	450	24	Avg. 180

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175