

CEWELD DUR CS

TYPE	Composite Nickel bronze alloy with tungsten particles
APPLICATIONS	The area to be hardfaced should be free of rust, scale, grease or other dirt. Slowly preheat the area to a maximum of 500°C (932°F). Sprinkle the surface with Ceweld Universal-Flux to prevent oxides from forming in the molten matrix during application. Once the area is properly heated, start brazing with L-CuNi10ZnF tinning rods (about 1 mm layer). Now apply Dur CS. To make brazing easier dip the end in the brazing flux. NOTE: Do not overheat the hardfaced area. Particles can be pushed in correct position and dense configuration by using the end of the tinning Rod. Slow cooling is advised. Never cool area with water!
PROPERTIES	Dur CS consists of sintered tungsten carbide fragments in a ductile Nickel Bronze Silver matrix. The alloy has a tensile strength of 80.000-100.000 psi. Dur CS production methods ensure an overall tinning of the sintered tungsten carbide particles. Dur CS composite rods are available in two grades: Wear resistant and for cutting applications. Melting point of 935°C.
CLASSIFICATION	
SUITABLE FOR	Downhole reamers, openers, fishing tools (spears), coring tools, reamers, milling tools, overshots, stabilizers, steel sawing, concrete drilling.
APPROVALS	No Approvals Found
WELDING POSITIONS	
REDRYING TEMPERATURE	Not required
GAS ACCORDING EN 14175	