




CEWELD E DUR 6U

TYPE	Cobalt-based welding electrode for overlay applications.						
APPLICATIONS	<p>CEWELD® DUR 6U is a Stellite 6 alloy with excellent properties against abrasion, thermal shock and corrosion in conjunction with high temperatures. It produces a high-quality armoring on components that are exposed to multiple stresses from erosion, corrosion, cavitation, pressure, impact, abrasion and high temperatures up to 900 °C, For example: sealing surfaces on fittings, valve seats and cones for combustion engines, metal-to-metal sliding surfaces, highly stressed hot working tools without thermal shock, grinding, stirring and drilling tools. drilling tools.</p>						
PROPERTIES	<p>CEWELD® DUR 6U has excellent welding properties and self-releasing slag. The weld metal can be machined with carbide tools and by grinding. The hardness of the weld metal decreases by 16 % at 300 °C and by around 30 % at 600 °C. The weld metal is highly heat-resistant up to 900 °C. Hardness of the pure weld metal: 40 - 42 HRC Hot hardness at 500 °C: approx. 30 HRC Hot hardness at 700 °C: approx. 160 HB</p>						
CLASSIFICATION	AWS	A 5.13: E CoCr-A					
	EN ISO	14700: E Co2					
	DIN	8555: E 20-UM-40- CTZ					
	F-nr	71					
SUITABLE FOR	Steam-valves, High temperature liquid pumps, Hot cutting tools, Exhaust valves, Pumps, Plastic recycling etc.						
APPROVALS	No Approvals Found						
WELDING POSITIONS							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Fe	W	Cr	Co
	1.1	1	0.6	2.5	4.5	28	Rem.
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	Hardness Rockwell C		
	As Welded /				Avg. 42		
REDRYING TEMPERATURE	300°C / 2 hr						
GAS ACCORDING EN 14175							



CEWELD E DUR 6U

E DUR 6U 2,5 X 350MM

Type	KG/unit	EANCode
Can	2,8	8720663402097

E DUR 6U 3,2 X 350MM

Type	KG/unit	EANCode
Can	2,8	8720663402103

E DUR 6U 4,0 X 350MM

Type	KG/unit	EANCode
Can	2,8	8720663402110