




CEWELD E NiFe 2

TYPE	Special "bimetal" core wire coated electrode for welding cast iron with high tensile strength.																					
APPLICATIONS	<p>CEWELD® E NiFe 2 is suitable for welding gray and malleable cast iron, as well as ductile cast iron. Use this type when high tensile strength is required or because of its non-overheating coating. Also suitable for joining steel to cast iron!</p> <p>For industrial applications such as: Power generation industry, overlay welding and repairs Construction and mechanical engineering, metallurgy (steelworks), mining, agriculture, lightweight construction.</p>																					
PROPERTIES	<p>CEWELD® E NiFe 2 offers several advantages compared to other "FeNi" grades due to improvements such as: weldable at very high current. The coating structure is not susceptible to overheating and produces a strong arc even at low amperages.</p> <p>If you cannot control the cooling rate, it is better to keep the workpiece at a low temperature during welding and hammer immediately after welding.</p>																					
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.15: E NiFe-CI</td> </tr> <tr> <td>EN ISO</td> <td>1071: E C NiFe-CI</td> </tr> </table>	AWS	A 5.15: E NiFe-CI	EN ISO	1071: E C NiFe-CI																	
AWS	A 5.15: E NiFe-CI																					
EN ISO	1071: E C NiFe-CI																					
SUITABLE FOR	<p>Spheroidal Cast Iron, Diluted Cast Iron, old Cast Iron, Steel to Cast Iron etc.</p> <p>EN 1561: EN-GJL-100, EN-GJL-150, EN-GJL-200, EN-GJL-250, EN-GJL-300, EN-GJL-350, GG10, GG15; GG20, GG25; GG30; GG35; GG40</p> <p>EN 1562: EN-GJMB-350, EN-GJMB-550 , EN- GJMW-350, EN- GJMW-550 , GTS 35, GTS 55, GTW 35, GTW 55</p> <p>EN1563: EN-GJS-400-15, EN-GJS-400-18, EN-GJS-450-10, EN-GJS-500-7, EN-GJS-600-3, EN-GJS-700-2. GGG40, GGG45, GGG50, GGG60; GGG70, GGG80</p>																					
APPROVALS	CE																					
WELDING POSITIONS																						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <tr> <td style="width: 25%;">C</td> <td style="width: 25%;">Si</td> <td style="width: 25%;">Mn</td> <td style="width: 25%;">Ni</td> <td style="width: 25%;">Fe</td> </tr> <tr> <td>1.5</td> <td>1.5</td> <td>1</td> <td>55</td> <td>42</td> </tr> </table>	C	Si	Mn	Ni	Fe	1.5	1.5	1	55	42											
C	Si	Mn	Ni	Fe																		
1.5	1.5	1	55	42																		
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <tr> <td style="width: 25%;">Heat Treatment</td> <td style="width: 10%;">R_{P0,2}</td> <td style="width: 10%;">R_m</td> <td style="width: 10%;">A₅</td> <td style="width: 10%;"> </td> <td style="width: 10%;"> </td> <td style="width: 20%;">Hardness</td> </tr> <tr> <td>As Welded /</td> <td>MPa</td> <td>MPa</td> <td>(%)</td> <td></td> <td></td> <td>Brinell Hardness</td> </tr> <tr> <td></td> <td></td> <td>400</td> <td></td> <td></td> <td></td> <td>Avg. 200</td> </tr> </table>	Heat Treatment	R _{P0,2}	R _m	A ₅			Hardness	As Welded /	MPa	MPa	(%)			Brinell Hardness			400				Avg. 200
Heat Treatment	R _{P0,2}	R _m	A ₅			Hardness																
As Welded /	MPa	MPa	(%)			Brinell Hardness																
		400				Avg. 200																
REDRYING TEMPERATURE	140°C / 2 hr																					
GAS ACCORDING EN 14175																						