





TYPE Special coated electrode for welding cast iron with a pure nickel core wire.

APPLICATIONS Joining and cladding grey and Malleable Cast Iron, also suitable for joint welds between steel,

Copper and Copper Alloys, especially for maintenance and repair.

PROPERTIES Excellent welding properties with easily controllable flow permits spatter free welding with very low

current. Due to the very low heat input and unique composition of CEWELD E Ni(-) the transition zone will stay well machinable and is therefore well suited to use as first layer in case off multi-layer welding. The weld metal will show no undercut !Preheating is normally done to slow down the cooling speed, in case you can not control the cooling speed it is better to keep the work peace at a

low temperature during welding and hammer immediately after welding.

CLASSIFICATION AWS A 5.15: E Ni-Cl

EN ISO 1071: E C Ni-Cl-1

SUITABLE FOR Grey Cast Iron, Malleable cast iron, EN 1561: EN-GJL-100 (GG10) till EN-GJL-350 (GG35), EN 1562:

EN-GJMB-350 (GTS 35) till EN-GJMB-550 (GTS 55), EN-GJMW-350 (GTW 35) till EN-GJMW-550

(GTW 55).

APPROVALS CE

WELDING POSITIONS

PA PB PC PD PE PF

TYPICAL CHEMICAL
ANALYSIS OF WELD METAL

ALL WELD MECHANICAL

PROPERTIES

(%)

C	Si	Mn	Ni	Fe	Cu
0.1	0.2	1.5	Rem.	2	1.5

Heat	R _{P0,2}	Rm	A5		Hardness
Treatment	MPa	MPa	(%)		Brinell Hardness
As Welded /				П	Ava. 160

REDRYING TEMPERATURE 140°C / 2 hr

GAS ACCORDING EN 14175





CEWELD E Ni(-)

E NI(-) 2,5 X 350MM	Type	KG/unit	EANCode	
	Can	3,5	8720663420558	_
E NI(-) 3,2 X 350MM	Type	KG/unit	EANCode	
	Can	3,5	8720663420565	_
E NI(-) 4,0 X 350MM	Type	KG/unit	EANCode	
	Can	3,5	8720663420596	_