





TYPE Rutile-coated stick electrode for heat-resistant stainless steels. (Type 25 20, 310)

APPLICATIONS CEWELD® 4842 Ti is for the dissimilar welding of heat-resistant rolled, forged and cast steels.

Common applications include industrial furnaces, annealing chambers, systems for treating molten

salts and boiler parts as well as heat exchangers.

PROPERTIES CEWELD 4842 Ti has good general oxidation resistance, especially at high temperatures, due to its

high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. In general the alloy is heat resistant up to  $1200\,^{\circ}$ C. This alloy can withstand relatively severe thermic shock, and is

superior to type 309 L.

CLASSIFICATION AWS A 5.4: E 310-16

EN ISO 3581-A: E 25 20 R 12

F-nr 5 FM 5 W.Nr. ~1.4842

SUITABLE FOR 1.4823, 1.4826, 1.4828, 1.4828, 1.4832, 1.4840, 1.4841, 1.4846, 1.4848, 1.4837, 1.4710, 1.4713, 1.4724,

Mn

1.4726, 1.4742, 1.4745, 1.4762, 1.4845, 1.4740

X15CrNiSi25-21, X8CrNi25-21, X15CrNiSi20-12, GX15CrNi25-20, X40CrNi25-21, GX40CrNiSi22-10,

X10CrAlSi7, X10CrAlSi13, X10CrAlSi18, X10CrAlSi25, GX30CrSi7, GX40CrSi17

AISI 305, 310, 314, ASTM A297 HF, A297 HJ

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL

ALL WELD MECHANICAL

PROPERTIES

Heat	R <sub>P0,2</sub>	Rm	A5	Impact Energy (J) ISO-V
Treatment	MPa	MPa	(%)	RT
Δs Welded /	380	600	30	75

0.015

0.02

REDRYING TEMPERATURE 300°C / 2 hr

GAS ACCORDING EN 14175

Fe

Rem.





## CEWELD 4842 Ti

4842 TI 2,0 X 300MM	Туре	KG/unit	EANCode
	Can	2,6	8720663415752
4842 TI 2,5 X 300MM	Type	KG/unit	EANCode
	Can	2,5	8720663415769
4842 TI 3,2 X 350MM	Type	KG/unit	EANCode
	Can	2,8	8720663415783
4842 TI 4,0 X 350MM	Type	KG/unit	EANCode
	Can	3,0	8720663415790
4842 TI 5,0 X 350MM	Type	KG/unit	EANCode
	Can	2,5	8720663415806