




CEWELD 310

TYPE	High heat resistant stainless steel welding wire														
APPLICATIONS	Common applications include industrial furnaces, annealing chambers, fused salt treatment installations and boiler parts, as well as heat exchangers.														
PROPERTIES	Solid drawn ,corrosion-resistant, chromium-nickel wire for welding heat-resistant austenitic steels of the 25% Cr, 20% Ni types. CEWELD 310 has good general oxidation resistance, especially at high temperatures, due to its high Cr content. The alloy is fully austenitic and is therefore sensitive to hot cracking. The temperature limits for use under intermittent oxidation depend on cycle frequency. This alloy can withstand relatively severe thermic shock, and is superior to type 309 L.														
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.9: ER310</td> </tr> <tr> <td>EN ISO</td> <td>14343-A: G 25 20</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> <tr> <td>W.Nr.</td> <td>1.4842</td> </tr> </table>	AWS	A 5.9: ER310	EN ISO	14343-A: G 25 20	F-nr	6	FM	5	W.Nr.	1.4842				
AWS	A 5.9: ER310														
EN ISO	14343-A: G 25 20														
F-nr	6														
FM	5														
W.Nr.	1.4842														
SUITABLE FOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30, Type: 25% Cr, 22%Ni 1.4710, 1.4713, 1.4724, 1.4726, 1.4742, 1.4745, 1.4762, 1.4823, 1.4826, 1.4828, 1.4832, 1.4835, 1.4837, 1.4840, 1.4841, 1.4845, 1.4846, 1.4848, 1.4849, 253MA, X15CrNiSi 25 20, G-X40CrNiSi 25 12, G-X15CrNi 25 20, X8CrNi25-21 AISI 305, 310, 314 ASTM A297 HF / A297HJ														
APPROVALS	CE														
WELDING POSITIONS															
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.5</td> <td>1.8</td> <td>26</td> <td>21</td> <td>0.3</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	0.1	0.5	1.8	26	21	0.3		
C	Si	Mn	Cr	Ni	Mo										
0.1	0.5	1.8	26	21	0.3										
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{p0,2} MPa</th> <th rowspan="2">R_m MPa</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> </tr> <tr> <th>RT</th> <th>-196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>395</td> <td>560</td> <td>45</td> <td>130</td> <td>40</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V		RT	-196°C	As Welded /	395	560	45	130	40
Heat Treatment	R _{p0,2} MPa					R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V							
		RT	-196°C												
As Welded /	395	560	45	130	40										
REDRYING TEMPERATURE	Not required														
GAS ACCORDING EN 14175	M13														



CEWELD 310

310 0,8MM

Type	KG/unit	EANCode
BS-300	15	8720663415998
D-200	5	8720663415837

310 1,0MM

Type	KG/unit	EANCode
BS-300	15	8720663416001
D-200	5	8720663416025
Drum	250	8720663416018

310 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663416032
D-200	5	8720663416049

310 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663416056