




CEWELD 410

TYPE	Solid stainless steel welding wire. (13% Cr Steel)																																
APPLICATIONS	Overlay of carbon and low-alloy steels for resistance to corrosion, erosion, or abrasion. 410 has higher hardness and is used in valve seats to obtain better galling resistance. Normally to obtain adequate ductility, preheat and post-weld heat-treatment are required.																																
PROPERTIES	CEWELD® 410 is a martensitic stainless steel that is heat-treatable. It has a nominal weld metal composition of 12% Chromium. These weld deposits are air-hardenable that can normally be heat-treated after welding.																																
CLASSIFICATION	AWS	A 5.9: ER410																															
	EN ISO	14343-A: G Z 13																															
	DIN	8555: MSG 5-GZ-CGTZ																															
	F-nr	6																															
	FM	5																															
	W.Nr.	1.4009																															
SUITABLE FOR	Ferritic 13 % Chrome steel, 1.4000, 1.4001, 1.4002, 1.4003, 1.4006, 1.4008, 1.4021, 1.4024, X6Cr13, X6CrAl13, X10Cr13, X15Cr13, X20Cr13, G-X10Cr13 AISI 410, 420																																
APPROVALS	CE																																
WELDING POSITIONS																																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Nb</th> <th>N</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.25</td> <td>0.4</td> <td>0.02</td> <td>0.001</td> <td>12.5</td> <td>0.2</td> <td>0.04</td> <td>0.01</td> <td>0.04</td> <td>0.05</td> </tr> </tbody> </table>											C	Si	Mn	P	S	Cr	Ni	Mo	Nb	N	Cu	0.1	0.25	0.4	0.02	0.001	12.5	0.2	0.04	0.01	0.04	0.05
C	Si	Mn	P	S	Cr	Ni	Mo	Nb	N	Cu																							
0.1	0.25	0.4	0.02	0.001	12.5	0.2	0.04	0.01	0.04	0.05																							
ALL WELD MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} MPa</th> <th>R_m MPa</th> <th>A₅ (%)</th> <th>Hardness Rockwell C</th> </tr> </thead> <tbody> <tr> <td>As Welded /1h</td> <td>400</td> <td>600</td> <td>22</td> <td>Avg. 35</td> </tr> </tbody> </table>										Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Hardness Rockwell C	As Welded /1h	400	600	22	Avg. 35													
Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Hardness Rockwell C																													
As Welded /1h	400	600	22	Avg. 35																													
REDRYING TEMPERATURE	Not required																																
GAS ACCORDING EN 14175	M20, M21, M11, C1																																



CEWELD 410

410 1,0MM

Type	KG/unit	EANCode
BS-300	15	8720663411884

410 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663411891

410 1,6MM

Type	KG/unit	EANCode
BS-300	15	8720663411907