

## CEWELD Al99,5 Ti

| TYPE  | Pure aluminum filler metal for Mig welding   |                   |     |     |      |     |      |
|---|--|-------------------|-----|-----|------|-----|------|
| APPLICATIONS  | Aluminium wire for welding mostly pure aluminium (maximum 0,5% of alloyed elements).<br>Applications in chemistry, electronics, construction and food industries.                    |                   |     |     |      |     |      |
| PROPERTIES  | This pure aluminum filler metal offers excellent weldability when properly cleaned prior to welding.<br>Heavy parts and thicker plates should be preheated (150°C), prior to welding |                   |     |     |      |     |      |
| CLASSIFICATION  | AWSA 5.10: ER1450EN ISO18273: S Al 1450 (Al99,5Ti)F-nr21   |                   |     |     |      |     |      |
| SUITABLE FOR  | Cast aluminium special repairs, Al99,0 Al.99,5 Al.99,7 E-Al.   |                   |     |     |      |     |      |
| APPROVALS   | CE   |                   |     |     |      |     |      |
| WELDING POSITIONS                                       |  |                   |     |     |      |     |      |
| TYPICAL CHEMICAL<br>ANALYSIS OF THE FILLER<br>METAL (%) | Si   |                   | Mn  |     | Ti   | Fe  | AL   |
|   | 0.2  | 0.01              |     |     | 0.15 | 0.2 | 99.6 |
| ALL WELD MECHANICAL                                     | Heat   | R <sub>P0,2</sub> | Rm  | A5  |      |     |      |
| PROPERTIES  | Treatment  | MPa               | MPa | (%) |      |     |      |
|   | As Welded /  | 30                | 80  | 40  |      |     |      |
| REDRYING TEMPERATURE                                    | Not required   |                   |     |     |      |     |      |

GAS ACCORDING EN 14175 I1, I3

Certilas The Filler Metal Specialist