



# CEWELD E NiCr 625 HLS

TYPE	Nickel based high recovery electrode. (Type 6625, ENiCrMo-3)																		
APPLICATIONS	<b>CEWELD® E NiCr 625 HLS</b> is developed for cladding Nickel-based alloys such as Alloy 625 or similar materials. This alloy can also be used for welding dissimilar nickel-based alloys to each other, to alloyed steels, to stainless steels and for joining 9% Nickel steels.																		
PROPERTIES	<b>CEWELD® E NiCr 625 HLS</b> have a very good resistance against pitting corrosion and crevice corrosion. Very good against acid, neutral or alkaline media, with or without chlorides. Very good resistance at high temperatures, especially against oxidation. High recovery of 140%																		
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.11: E NiCrMo-3</td> </tr> <tr> <td>EN ISO</td> <td>14172: E Ni 6625 (NiCr22Mo9Nb)</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> <tr> <td>W.Nr.</td> <td>2.4621</td> </tr> </table>	AWS	A 5.11: E NiCrMo-3	EN ISO	14172: E Ni 6625 (NiCr22Mo9Nb)	F-nr	43	FM	6	W.Nr.	2.4621								
AWS	A 5.11: E NiCrMo-3																		
EN ISO	14172: E Ni 6625 (NiCr22Mo9Nb)																		
F-nr	43																		
FM	6																		
W.Nr.	2.4621																		
SUITABLE FOR	<p><b>Ni 6625 / NiCr22Mo9Nb / 2.4831</b>  <b>W.Nr:</b> 1.4529, 1.4539, 1.4547, 1.4876, 1.4958, 1.5656, 2.4660, 2.4816, 2.4856, 2.4858,</p> <p>X1CrNiMoCuN20-18-7 - X10NiCrAlTi32-20 - X5NiCrAlTi31-20 - NiCr15Fe - NiCr22Mo9Nb - NiCr21Mo - X1NiCrMoCuN25 20 6 - X1NiCrMoCuN25 20 5 - NiCr21Mo - 8XNi9  <b>ASTM:</b> A 533 Gr1, B443, B444, B446  <b>UNS:</b> S31254 - N08800 - N08810 - N06600 - N06625 - N08825 - N08926 - N08020  Alloy 254 SMO - Alloy 800 - Alloy 800H - Alloy 600 - Alloy 625 - Alloy 825 - Sanicro 28</p>																		
APPROVALS	No Approvals Found																		
WELDING POSITIONS																			
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Fe</th> <th>Nb+Ta</th> <th>Nb</th> </tr> </thead> <tbody> <tr> <td>0.08</td> <td>0.6</td> <td>0.7</td> <td>22</td> <td>60</td> <td>9</td> <td>5</td> <td>4</td> <td>3.8</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	Fe	Nb+Ta	Nb	0.08	0.6	0.7	22	60	9	5	4	3.8
C	Si	Mn	Cr	Ni	Mo	Fe	Nb+Ta	Nb											
0.08	0.6	0.7	22	60	9	5	4	3.8											
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R<sub>p0,2</sub> MPa</th> <th>R<sub>m</sub> MPa</th> <th>A<sub>5</sub> (%)</th> <th>RT</th> <th>Impact Energy (J) ISO-V -196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded /</td> <td>455</td> <td>795</td> <td>37</td> <td>78</td> <td>60</td> </tr> </tbody> </table>	Heat Treatment	R <sub>p0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	RT	Impact Energy (J) ISO-V -196°C	As Welded /	455	795	37	78	60						
Heat Treatment	R <sub>p0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	RT	Impact Energy (J) ISO-V -196°C														
As Welded /	455	795	37	78	60														
REDRYING TEMPERATURE	300°C / 2 hr																		
GAS ACCORDING EN 14175																			



# CEWELD E NiCro 625 HLS

E Nicro 625 HLS 2,5 X  
350MM

Type	KG/unit	EANCode
Can	2,27	8720663418746

E Nicro 625 HLS 3,2 X  
350MM

Type	KG/unit	EANCode
Can	2,27	8720663418753

E Nicro 625 HLS 4,0 X  
350MM

Type	KG/unit	EANCode
Can	2,27	8720663418760