

CEWELD Alloy C-2000 Tig

TYPE Nickel based wire rod for welding similar NiCrMo alloys

APPLICATIONS CEWELD Alloy C-2000 Tig (UNS N06200) is unique among the versatile nickel-chromium-molybdenum materials in having a deliberate copper addition

PROPERTIES Like other nickel alloys, it is ductile, easy to form and weld, and possesses exceptional resistance to stress corrosion cracking in chloride-bearing solutions (a form of degradation to which the austenitic stainless steels are prone). It is able to withstand a wide range of oxidizing and non-oxidizing chemicals, and exhibits outstanding resistance to pitting and crevice attack in the presence of chlorides and other halides.

CLASSIFICATION

AWS	A 5.14: ERNiCrMo-17
EN ISO	18274: S Ni 6200(NiCr23Mo16Cu2)
F-nr	43
FM	6
W.Nr.	2.4675

SUITABLE FOR Alloy C-2000

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)


C	Si	Mn	Cr	Ni	Mo	Fe	Co	Cu
0.01	0.08	0.4	23	60	16	2	1	1.5

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	
As Welded /	280	690	45	

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1



CEWELD Alloy C-2000 Tig

ALLOY C-2000 TIG 1,6 X
914MM

Type	KG/unit	EANCode
Tube	4,54	8720663419958

ALLOY C-2000 TIG 2,4 X
914MM

Type	KG/unit	EANCode
Tube	4,54	8720663419965