



CEWELD S2Si

TYPE Solid wire for submerged arc welding up to 420 MPa yield strength structural steels

APPLICATIONS Shipbuilding, piping, root welding, bridges, repair, construction, offshore, etc.

PROPERTIES Solid drawn and rolled SAW wire with copper coating for improved current carrying capacity. S2 wire can be used with FL 180, FL188, FL 155 and FL 851 depending on the requirements and application.

CLASSIFICATION

AWS	A 5.17: EM12K
AWS	A 5.23: EM12K
EN ISO	14171-A: S2Si
F-nr	6
FM	1

SUITABLE FOR A, B, D, E, St 37 - St 52-3, DIN 17 100, H I, H II, 17Mn4, 16Mo5, DIN 17 155, StE 255 - StE 355, DIN 17 102, GS-38, GS-60, DIN 1681, St 35.8, St 45.8, DIN 17 175, St 37.0 - St 52.0, DIN 1626 / 1629, St 37.4 - St 52.4, DIN 1628 / 1630, StE 290.7 TM - StE 360.7 TM, DIN 17 172, X 52

APPROVALS CE

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S
0.1	0.3	1.1	0.015	0.015

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V	
				0°C	-20°C
As Welded /1h	460	600	22	60	50

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175