



ТҮРЕ	Medium -alloyed seamless fluxcored wire on a C-Cr-Mo-W-V basis offering high hardness up to 550°C.						
APPLICATIONS	Recommended for parts subject to strong mineral abrasion and erosion that faces increased working temperatures up to 450°C.						
PROPERTIES	Very good abrasion resistance in combination with impact even at higher temperatures up to 550°C. To much layers should be avoided, preheat is necessary to avoid cracking. A buffer layer with AA M690 or AA M37-42 is recommended in case of sensible base material or old hardfacing layers.						
CLASSIFICATION	AWSA 5.21: ERFe-8EN ISO14700: T Fe8DINMSG 3-GF-60-GPZW.Nr.~1.2606						
SUITABLE FOR	HRc 58-62, Cement pumps, crusher bars, hammer and blooming table rolls, mineral and brick industry, stone crushers.						
APPROVALS	No Approvals Found						
WELDING POSITIONS							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C Si 0.5 1.25	Mn Cr 1.3 5.7	Mo 1.4	V 0.3	Fe Rem.	W 1.3	
ALL WELD MECHANICAL PROPERTIES	Heat R _{P0,2} Treatment MPa	Rm A5 MPa (%)		Hardnes Rockwell			

REDRYING TEMPERATURE Not required

As Welded /

GAS ACCORDING EN 14175 M21

Certilas THE FILLER METAL SPECIALIST

Avg. 59





CEWELD AA M650

AA M650 1,2MM	Туре	KG/unit	EANCode
	BS-300	15	8720663424198