





# CEWELD E DUR 64

TYPE	Basic coated, high Chromium-Niobium based Hardfacing high recovery hardfacing electrode								
APPLICATIONS	This electrode with a recovery of 190% can be used for overlays with extremely abrasive and sliding wear resistance, but with middle impact.								
PROPERTIES	Due to the high Mo-content, abrasion resistance can be kept up to working temperatures of 600 °C ; the hardness is still 40-45 HRC at these temperatures. For Hardfacing of more than 3 layers it is necessary to buffer with an electrode like CEWELD® E DUR 350 Kb that delivers a welding deposit of less hardness. Overlays on steel with high tensile strength have to be buffered with CroNi 29/9 HL or 4370 HL. Equivalent in FCAW: CEWELD® OA 64								
CLASSIFICATION	AWS	A 5.13: E FeCr-E4							
	EN ISO	14700: E Fe16							
	DIN	8555: E 10-UM-65- GTZ							
	F-nr	71							
SUITABLE FOR	Sugar mill knives and Hammers, Clinker crushers, Sintering lines, Fire gratings, Mixer blades, Gravel washing equipment, Ceramic mixer blades, Mill rollers, Stone crushers, Cxtruders etc....								
APPROVALS	No Approvals Found								
WELDING POSITIONS	<div></div>								
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Mn	Cr	Mo	Nb	V	Fe	W	Si
	5.5	0.6	24	6	6	1	Rem.	2	0.9
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R <sub>p0,2</sub> MPa	R <sub>m</sub> MPa	A5 (%)			Hardness Rockwell C		
	As Welded /						Avg. 61		
REDRYING TEMPERATURE	300°C / 2 hr								
GAS ACCORDING EN 14175									



# CEWELD E DUR 64

E DUR 64 3,2 X 350MM

Type	KG/unit	EANCode
Can	2,4	8720663402677

E DUR 64 4,0 X 450MM

Type	KG/unit	EANCode
Can	3,0	8720663402684

E DUR 64 5,0 X 450MM

Type	KG/unit	EANCode
Can	2,9	8720663402691