



CEWELD AA M CrMo1V TIG

TYPE Seamless metal cored wire Tig Rod. (Typ CrMo1V, 1.7745)

APPLICATIONS Foundries, production welding

PROPERTIES CEWELD® AA M CrMo1V TIG is a metal cored wire wire tig Rod with Excellent weld puddle manipulation. Without slag. Extremely crack resistant. Suitable for economic welding of CrMoV-steels up to 550 °C. Due to the seamless production process the hydrogen content is below 3ml/100g weld metal even after long storage in unconditioned condition. Good gap bridging properties.

CLASSIFICATION

AWS	A 5.28: ER80T15-GM2M H4
AWS	A 5.36: ER80T15-M21PY-G-H4
EN ISO	17634-A: ~ WT Z M M 1 H5
F-nr	6
FM	4
W.Nr.	~1.7745

SUITABLE FOR **Typ 1Cr0,5Mo,V ISO 15608: ~5,1**
 1.7335, 1.7262, 1.7728, 1.7218, 1.7225, 1.7258, 1.7354, 1.7357, 1.7745, 1.7706, 1.7733
 13CrMo4-5, 15CrMo5, 15 CrMoV 5 10, 16CrMoV4, 25CrMo4, 42CrMo4, 24CrMo5, G22CrMo5-4,
 G17CrMo5-5, 24CrMoV5-5, G17CrMoV5-10
 ASTM A 182 Gr. F12; A 193 Gr. B7; A 213 Gr. T12; A 217 Gr. WC6; A 234 Gr. WP11; A335 Gr. P11,
 P12; A 336 Gr. F11, F12; A 426 Gr. CP12

APPROVALS No Approvals Found

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo	V
0.1	0.3	0.9	0.015	0.015	1.1	0.3	1	0.25

ALL WELD MECHANICAL PROPERTIES

Heat Treatment	R _{p0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V RT
690°C±15°C /6h	550	700	20	70

REDRYING TEMPERATURE Not required

GAS ACCORDING EN 14175 I1