



CEWELD 16.8.2 Tig

TYPE	A specially designed hybrid alloy between 308H and 316H for high temperature applications.								
APPLICATIONS	Used mainly in power generation and chemical process industries on applications such as, steam turbines, catalytic crackers, transfer piping and furnace accessories.								
PROPERTIES	A specially designed composition where Molybdenum % is reduced to form a hybrid alloy between 308H and 316H, operates in temperatures up to 800 °C. CEWELD® 16.8.2 Tig gives a very high resistance to thermal embrittlement. Creep ductility is enhanced at temperatures above 650 °C.								
CLASSIFICATION	AWS	A 5.9: ER16-8-2							
	EN ISO	14343-A: W 16 8 2							
	F-nr	4							
	FM	5							
SUITABLE FOR	1.4948, 1.4941, 1.4961, 1.4919, X6CrNi18-10, X8CrNiTi18-10, X8CrNiNb16-13, X6CrNiMoB17-12-2, 304H, 321H , 347H, 316H, UNS 30409, S32109,S34709, S31609, 304S51, 321S51, 347S51, 316S51, 316S53								
APPROVALS	CE								
WELDING POSITIONS									
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu
	0.05	0.4	1.3	0.01	0.003	15.3	8.4	1.2	0.02
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0.2} MPa	R _m MPa	A5 (%)	Impact Energy (J) ISO-V -196°C				
	As Welded /	420	850		90				
REDRYING TEMPERATURE	Not required								
GAS ACCORDING EN 14175	I1, I3								



CEWELD 16.8.2 Tig

16.8.2 TIG 2,4 X 1000MM

Type	KG/unit	EANCode
Tube	5	8720663413253