





# CEWELD ERTi-5 (spool)

TYPE	Titanium Tig welding wire grade 5							
APPLICATIONS	Aerospace, marine, chemical plants, process plants, power generation, oil and gas extraction, medical and sports.							
PROPERTIES	Excellent weldability, and can be heat treated to a higher strength or toughness. Grade 5 is used in aircraft components such as landing gear, wing spars, and compressor blades. Its corrosion resistance is generally comparable to Grade 2 and it is often used in corrosion service where higher strength is required, particularly in shafts, high strength bolting, and keys. The weld deposit is ductile and offers excellent corrosion resistance in oxidizing environments. The unique combination of mechanical strength and corrosion resistance makes the alloy a preferred choice in many applications to prevent or solve problems. The wire is cleaned in a very special way to obtain porosity free and a ductile weld deposit.							
CLASSIFICATION	AWS	A 5.16: ERTi-5						
	EN ISO	24034: S Ti 6402 / TiAl6V4B						
	F-nr	51						
SUITABLE FOR	Titanium grade 5, UNS R56400, AMS 4954							
APPROVALS	No Approvals Found							
WELDING POSITIONS	<div>  </div>							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	V	H	N	O	Fe	Al	Ti
	0.023	4.11	0.0029	0.011	0.088	0.1	6.11	Rem.
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A5 (%)				
	As Welded /	810	890					
REDRYING TEMPERATURE	Not required							
GAS ACCORDING EN 14175	I1							



## CEWELD ERTi-5 (spool)

ERTI-5 (SPOOL) 0,8MM

Type	KG/unit	EANCode
D-300	10	8720663406514

ERTI-5 (SPOOL) 1,0MM

Type	KG/unit	EANCode
D-300	10	8720663406521

ERTI-5 (SPOOL) 1,2MM

Type	KG/unit	EANCode
D-300	10	8720663406538