



CEWELD E 11018-M

TYPE	High-strength basic coated stick electrode with extremely low H2 content in the weld metal (Type 11018)				
APPLICATIONS	CEWELD® E 11018-M is a Mn, Ni, Cr and Mo alloyed highly basic electrode for welding low-alloy steels with a tensile strength ≤ 700 MPa. Used in offshore, crane construction, heavy transport machinery, lifting equipment, etc.				
PROPERTIES	CEWELD® E 11018-M is crack resistant and well suited for low temperatures. It shows very good ductility down to -60 °C. The preheating, interpass temperature and post-weld treatment should be selected as for the base metal. The hydrogen content is HD < 3 ml/100 g in the weld metal.				
CLASSIFICATION	AWS	A 5.5: E 11018-M			
	EN ISO	18275-A: E 69 5 Mn2NiMo B 42 H5			
	F-nr	4			
	FM	2			
SUITABLE FOR	1.8914, 1.8927, 1.8931, 1.8928, 1.7147, 1.7149, 1.8734 S620Q, S620QL, S690Q, S690QL, S620QL1-S690QL1 L480 - L550, X65, X80, X90, X100, HY 80, HY 100 ASTM A 514 Gr. F, H, Q; A 709 Gr. 100 Type B, E, F, H, Q; A 709 Gr. HPS 100W Weldox 700, Dillimax 690, Hardox, Naxtra 63, Naxtra 70, Optim 700 mc plus, Weldox 500, Hardox, Domex 460 MC, Domex 500 MC, Domex 550 MC, Domex 600 MC, Domex 650 MC, Domex 700 MC, Hardox 400, XAR 400, Dillidur 400, Oceanfit 100, Oceanfit 690, alform plate 620 M, 700 M, aldur 620 Q, 620 QL, 620 QL1, aldur 700 Q, 700 QL, 700 QL1				
APPROVALS	CE				
WELDING POSITIONS	PAPBPCPEPF				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Ni	Mo
	0.06	0.3	1.5	2.2	0.4
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} MPa	R _m MPa	A ₅ (%)	Impact Energy (J) ISO-V -50°C
	As Welded /	705	770	20	65
REDRYING TEMPERATURE	300°C / 2 hr				
GAS ACCORDING EN 14175	None				



CEWELD E 11018-M

E 11018-M 2,5 X 300MM

Type	KG/unit	EANCode
Vacuum	1,8	8720682051368

E 11018-M 3,2 X 350MM

Type	KG/unit	EANCode
Vacuum	2,0	8720663424785

E 11018-M 4,0 X 450MM

Type	KG/unit	EANCode
Vacuum	2,8	8720682051351