



CEWELD AA M37-42

TYPE	Seamless medium alloyed metal powder fluxcored wire without slag for hardfacing using Ar-CO2 Mixgas				
APPLICATIONS	375-450 HB, hardfacing and rebuilding alloy for wornout wheels, rails, tires, conveyors, crossings, shafts, bufferlayers prior to hardfacing. excelent wear and abrasion resistance against heavy impact and shock, machinable with carbide tools.				
PROPERTIES	Due to the high resistance to cracking and excelent toughness, all weld metal requires no buffer layer except on materials considered critical. Suited for wear parts subject to heavy impact and shock. The interpass temperature should be maximum 250°C. The weld metal is machinable with carbide tip tools, hardening is possible. The maximum hardness is dependent on the base metal and is achieved already in the first layer.				
CLASSIFICATION	EN ISO	14700: T ZFe2			
	DIN	8555: MF 1-GF-40 GPS			
SUITABLE FOR	Conveyors and transport surfaces, tires, bucket and loader teeth, cruscher jaws, Bufferlayers, crane wheels, axis, gear parts, winches etc.				
APPROVALS	No Approvals Found				
WELDING POSITIONS					
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	Cr	Mo
	0.4	0.7	1.5	2.5	0.5
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R _{p0,2} MPa	R _m MPa	A5 (%)	Hardness Rockwell C
	As Welded /				Avg. 40
REDRYING TEMPERATURE	Not required				
GAS ACCORDING EN 14175	M21				



CEWELD AA M37-42

AA M37-42 1,2MM

Type	KG/unit	EANCode
BS-300	15	8720663423214

AA M37-42 1,6MM

Type	KG/unit	EANCode
K-300	15	8720663423221