








# CEWELD E DUR 350 Kb

TYPE	Basic coated electrode for hardfacing machine parts, buffer layers and rebuilding rails and crossings..				
APPLICATIONS	Hardfacing and rebuilding machine parts that faces high impact and wear. The alloy is also excellent for buffer layers prior to Hardfacing.				
PROPERTIES	CEWELD® E DUR 350 Kb is a Hardfacing electrode against high impact combined with abrasion. This alloy has no risk for cracks and can also be applied on austenitic manganese steels. The weld deposit is good machinable. Very good weld deposit appearance and outstanding welding properties on both AC and DC+. Preheating is not required. Outstanding slag release.				
CLASSIFICATION	EN ISO	14700: E Fe1			
	DIN	8555: E 1-UM-350-P			
SUITABLE FOR	Rebuilding worn machine parts such as, Rails, Crossings, Wheels, Dredging parts, Stone crushers, Hammers, Gears, Cams, Bearings, Rope winches etc.				
APPROVALS	No Approvals Found				
WELDING POSITIONS	<div>    </div>				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Mn	Ni	Fe	Si
	0.15	1.1	3	Rem.	0.7
ALL WELD MECHANICAL PROPERTIES	Heat Treatment	R <sub>p0,2</sub> MPa	R <sub>m</sub> MPa	A <sub>5</sub> (%)	Hardness Brinell Hardness
	As Welded /				Avg. 370
REDRYING TEMPERATURE	140°C / 2 hr				
GAS ACCORDING EN 14175					



# CEWELD E DUR 350 Kb

E DUR 350 KB 2,5 X 350MM	Type	KG/unit	EANCode
	Can		8720663401564
E DUR 350 KB 3,2 X 350MM	Type	KG/unit	EANCode
	Can	2,8	8720663401571
E DUR 350 KB 4,0 X 450MM	Type	KG/unit	EANCode
	Can	3,5	8720663401588
E DUR 350 KB 5,0 X 450MM	Type	KG/unit	EANCode
	Can	3	8720663401595