

# CEWELD SS 6356

TYPE	Cobalt alloyed age hardenable hardfacing alloy for MIG welding.																													
APPLICATIONS	<p>CEWELD® SS 6356 is a hardenable, high-alloy material suitable for highly wear-resistant cladding in conditions involving abrasion and high working temperatures.</p> <p>Its main application is to create highly wear-resistant clad layers on cold and hot working tools. It is used for the repair and preventive maintenance of highly stressed cold and hot working tools, such as punching dies, cold and hot cutting knives, aluminium die cast moulds, cold forging dies, and drawing, stamping and chamfering tools.</p>																													
PROPERTIES	CEWELD® SS 6356 can be machined in the welded condition, and subsequent artificial aging optimizes resistance to hot wear and temperature changes.																													
CLASSIFICATION	EN ISO 14700: S Fe5 W.Nr. ~1.6356																													
SUITABLE FOR	All hot- and cold-work steels. GG and GGG cast iron materials. Similar materials: 1.2706 / 1.2709 / Böhler W720/21/22 / 1.6354 / 1.6358 (AMS 6512-6514) / Thyrodur / Corrax.																													
APPROVALS	No Approvals Found																													
WELDING POSITIONS	 PA  PB  PC  PD  PE  PF																													
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th><th>Si</th><th>Mn</th><th>Cr</th><th>Ni</th><th>Mo</th><th>Ti</th><th>Fe</th><th>Rem.</th><th>Co</th></tr> </thead> <tbody> <tr> <td>0.01</td><td>0.4</td><td>0.03</td><td>0.2</td><td>18</td><td>4</td><td>1.6</td><td></td><td></td><td>12</td></tr> </tbody> </table>										C	Si	Mn	Cr	Ni	Mo	Ti	Fe	Rem.	Co	0.01	0.4	0.03	0.2	18	4	1.6			12
C	Si	Mn	Cr	Ni	Mo	Ti	Fe	Rem.	Co																					
0.01	0.4	0.03	0.2	18	4	1.6			12																					
ALL WELD MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th><th>R<sub>P0,2</sub> MPa</th><th>R<sub>m</sub> MPa</th><th>A5 (%)</th><th></th><th></th><th></th><th>Hardness Rockwell C</th><th></th><th></th></tr> </thead> <tbody> <tr> <td>As Welded /</td><td>880</td><td>980</td><td></td><td></td><td></td><td></td><td>Avg. 38</td><td></td><td></td></tr> </tbody> </table>										Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A5 (%)				Hardness Rockwell C			As Welded /	880	980					Avg. 38		
Heat Treatment	R <sub>P0,2</sub> MPa	R <sub>m</sub> MPa	A5 (%)				Hardness Rockwell C																							
As Welded /	880	980					Avg. 38																							
REDRYING TEMPERATURE	Not required																													
GAS ACCORDING EN 14175	I1, M12, M13																													